

Trade name: **COPLAST-AS**
 Date of printing: 22.10.2012

Revision: 05 / 2012

COPLAST-AS	
Data sheet update	05 / 2012
Density, g/cm ³ , DIN EN ISO 1183	0.670
Elongation at yield, %, DIN EN ISO 527	3
Yield stress, MPa, DIN EN ISO 527	18
Tensile modulus of elasticity, MPa, DIN EN ISO 527	1100
Biege-E-Modul, MPa, DIN EN ISO 178	1400
Impact strength, KJ/m ² , DIN EN ISO 179	23
Shore hardness D, DIN EN ISO 868	70
Mean coefficient of linear thermal expansion, K ⁻¹ , DIN 53752	0,83 × 10 ⁻⁴
Fire behaviour DIN 4102	DIN 4102 B2 normal flammability (self-assessment without test certificate), DIN 4102 B1 low flammability for 10 mm available upon request, general test certificate issued by an approved building inspectorate (Germany)
Fire behaviour NF P 92-501	NF P 92-501 M1 for 10 mm available upon request
Surface resistivity, Ohm, DIN IEC 60093	<= 10 ¹²
Temperature range, °C	0 to +60
Physiological safety in accordance with BfR (German Federal Institute for risk valuation)	no
Physiological safety in accordance with EU	no
Physiological safety in accordance with FDA	no

The data presented in this section are to be seen as a guide and may vary depending on the processing method and test specimen used. In general, the figures are averages of tests performed on extruded sheets with a thickness of 4 mm. In the case of sheets manufactured by means of pressing, testing is generally performed on sheets with a thickness of 20 mm. Deviations may be possible if sheets are not available in these specific thicknesses. In the case of backed sheets, all technical specifications relate to the non-backed base sheets. Please note that this information is not necessarily applicable to products that have undergone downstream processing. The suitability of a material for a specific area of application must be checked by the processor or end user. All technical specifications are provided only as a guide for planning purposes. They do not constitute a guarantee of specific properties or qualities. For further information, please contact our Technical Service Centre at tsc@simona.de.

